

Cypress Semiconductor Qualification Report

QTP# 98446 VERSION 1.0
February, 1999

32 Ld, 300-mil SOJ Package

(CY7C1009 Rev. H)

Cypress Philippines Assembly

CYPRESS TECHNICAL CONTACT FOR QUALIFICATION DATA:

Cypress Semiconductor – Quality & Reliability Department
(408) 432-7069

PLASTIC PACKAGE/ASSEMBLY DESCRIPTION			
Package Outline, Type, or Name:	32 Ld, 300-mil SOJ (CY7C1009 Rev. H)		
Mold Compound Name/Manufacturer:	Sumitomo EME 7351		
Lead Frame material:	Copper		
Lead Finish, composition:	Solder Plated, 85%Sn, 15%Pb		
Die Attach Area Plating:	Silver		
Die Attach Method:	Epoxy	Die Attach Material:	Ablestik 8361H
Wire Bond Method:	Thermosonic	Wire Material/Size:	Gold / 1.0 mil
JESD22-A112 Moisture Sensitivity Level	Level 2		
Assembly Line ID and Process ID:	Cypress Philippines (CSPI-R)		

Note: Please contact a Cypress Representative for other packages availability.

RELIABILITY TESTS PERFORMED

Stress/Test	Test Condition (Temp/Bias)	Result P/F
Temperature Cycle	MIL-STD-883C, Method 1010, Condition C, -65°C to 150°C Precondition: JESD22 Moisture Sensitivity Level 2 168 Hrs., 85°C/60%RH	P
High Accelerated Saturation Test	140°C/5.5V Precondition: JESD22 Moisture Sensitivity Level 2 168 Hrs., 85°C/60%RH	P
Acoustic Microscopy Test (C-SAM)	Cypress Spec 25-000104	P

RELIABILITY TEST DATA

QTP#: 98446¹

DEVICE	ASSY-LOC	FABLOT#	ASSYLOT#	DURATION	S/S	REJ	FAIL MODE
STRESS: HI-ACCEL SATURATION TEST (140C, 5.5V), PRECOND. 168 HRS 85C/60%RH							
CY7C1009-VC	CSPI-R	4833174	619811835	128	45	0	
STRESS: TC COND. C, -65 TO 150C, PRECOND. 168 HRS 85C/60%RH							
CY7C1009-VC	CSPI-R	4819961	619811577	300	46	0	
CY7C1009-VC	CSPI-R	4819961	619811577	1000	46	0	
CY7C1009-VC	CSPI-R		619811745	300	46	0	
CY7C1009-VC	CSPI-R	4833174	619811835	300	46	0	

¹ Qtp 98446, 32-pin, 300 mil SOJ was qualified at Cypress Philippines with MSL 2 using CY7C1009 rev H (R42HD technology).

PACKAGE RELATED RELIABILITY TEST DATA

QTP#: 98223²

DEVICE	ASSY-LOC	FABLOT#	ASSYLOT#	DURATION	S/S	REJ	FAIL MODE
STRESS: HI-ACCEL SATURATION TEST (140C, 5.5V), PRECOND. 168 HRS 85C/85%RH							
CY7C1009-VC	CSPI-R	4742827	619710919	128	45	0	
STRESS: HIGH TEMPERATURE STORAGE (165C, NO BIAS)							
CY7C1009-VC	CSPI-R	4742827	619710919	336	45	0	
STRESS: TC COND. C, -65 TO 150C, PRECOND. 168 HRS 85C/85%RH (MSL 1)							
CY7C1009-VC	CSPI-R	4742827	619710919	300	45	0	
CY7C1009-VC	CSPI-R	4742817	619710920	300	45	0	
CY7C1009-VC	CSPI-R	4742844	619710921	300	45	0	
STRESS: THERMAL SHOCK, CONDITION B							
CY7C1009-VC	CSPI-R	4742827	619710919	100	45	0	
CY7C1009-VC	CSPI-R	4742827	619710919	200	45	0	

² Qtp 98223, 32-pin, 300 mil SOJ was qualified at Cypress Philippines with MSL 3 using CY7C1009 rev G (R32D technology).